

Baerlocher Additives for PVC **Cables and Wires**







we add character to plastics

The Baerlocher Group of Companies is one of the world's leading suppliers of additives for the plastics industry with a strong focus on PVC. Baerlocher has extensive technology and market knowledge drawn from more than 190 years of company history.

Additives play a crucial role in determining processing properties as well as product quality and character. Baerlocher offers a broad range of additives for polymers suitable for various industries.

Baerlocher is your global partner for Ca-based solutions and metal soaps.

By developing and supplying innovative additives, Baerlocher enables the plastics industry worldwide to manufacture high-quality and sustainable products.

www.baerlocher.com



Sixteen production sites in Germany, United Kingdom, Italy, France, San Marino, Turkey, the United States, China, Malaysia, Korea, India, Brazil, Peru and Argentina as well as a worldwide sales network make the Baerlocher group of companies a strong partner. This global presence and 1150 employees worldwide make sure that we are always close to the customer. Future-oriented, we are continuously investing in research and development. Our innovative power results from the creativity of our in-house scientists and technical experts. Baerlocher has R&D facilities all over the world.

Sustainable development, safe and environmentally friendly production processes as well as protection of people and the environment are key corporate goals. Our quality management system with ISO 9001 certification, our environmental management system with ISO 14001 certification and our energy saving management system ISO 50001 certification encourage all employees to act responsibly in order to achieve joint success with our customers.

Baerlocher products

BAEROPANBAEROCIDBAEROSTABBAEROCINBAEROPOLCEASITBAEROLUBZINCUMBAEROPHOBCEASIT

BÆRLOCHER



Additives for the Extrusion of PVC Cables and Wires

Plasticized PVC has been used to produce cable and wire insulation and sheathing for more than 50 years. It is still enjoying a healthy worldwide market share of the electrical insulation materials currently in use. Development and use of stabilizer systems are determined by a number of factors, including technical, ecological and political interests and, not least, emotional forces. During a transitional period of time three different systems are currently used at the same time: Lead, Barium/Zinc, Calcium/Zinc. They compete with each other in terms of stabilising costs, performance and processing properties. In addition, ecological considerations and statutory requirements on national and European levels become increasingly important.

Baerlocher PVC additives allow cables and wires of high quality to be made efficiently, imparting to the finished products specific performance characteristics, such as good heat stability. Baerlocher develops tailor-made products to suit the needs of each individual customer and manufacture them at one of the worldwide production sites. Special emphasis is always placed on customer focus and consistent quality. We offer a full range of stabilizers, from proven Lead stabilizers to the meanwhile generally accepted Calcium/Zinc stabilizers. All stabilizer types are available in various supply forms ranging from powders to one-packs in granule form.



Baerlocher PVC Additives

- high-performance
- tailor-made
- quality-controlled
- future-orientated
- cost-efficient

Contents

- 7 Application: 70 °C
- 8 Application: 90 °C
- 9 Application: 105 °C/125 °C
- 12 Transparent cables
- 14 Overview





Application 70 °C

Calcium/Zinc

Baeropan MC or R-KA 81/5 Baeropan MC or R-KA 83/5

These are Baerlocher's standard Calcium/Zinc one-packs for cable sheathing. They match the heat stability of onepacks based on lead sulfate like Baeropan E 292 KA when used at the same dosage. Baeropan MC or R KA-83/5, for example, is a product modification giving significantly improved early colour in white or lightpigmented cables.

Baeropan MC or R 8703 KA/5

Baeropan MC or R 8850 KA/5

Both products have been developed for use in standard insulation compounds. They ensure very low water absorption of the finished cable.

Water absorption

Baeropan R-KA 81/5	Baeropan R 8703 KA/5
2.05 wt%	0.65 wt%

According to IEC 811-1-3, 9.2 (70 °C, 14 days)

Comparison of Calcium/Zinc and Lead (service temperature max. 70 °C)

Mathis oven test at 200 °C



Application 90 °C

Calcium/Zinc

Baeropan MC or R 8656 KA-ST Baeropan MC or R 8823 KA Baeropan MC or R 8937 KA

These Calcium/Zinc stabilizers ensure excellent electrical properties, very good colour hold, outstanding heat stability and good heat ageing properties of the finished products. They are mainly used in cable insulation. All properties, including very low water absorption, are equivalent to those of known standard Lead stabilizers like Baeropan TX 770 KA.

Baeropan MC or R 8656 KA-ST is also very well suited for use in flame retardant compounds.

Comparison of Calcium/Zinc and Lead (service temperature max. 90 °C)

Mathis oven test at 200 °C



Calcium/Zinc

Baeropan MC or R 8553 KA-ST/3 (105 °C) Baeropan MC or R 8890 KA/2 (125 °C)

These Calcium/Zinc stabilizers are used in high-temperature cables. They are similar to lead phthalate one-packs like Baeropan MC 1978 KA in terms of water absorption and, consequently, electrical properties. Baeropan MC or R 8890 KA/2 was specially developed for a dosage above 12 phr and meets the stringent requirements of 125 °C applications. It covers automotive applications according to ISO/DIS 6722 class C.

Although these products already contain lubricants, it may be necessary to improve their rheological performance to meet specific customer requirements. This can be done with various lubricant systems, for example with products from the Baerolub range.

Comparison of Calcium/Zinc and Lead (service temperature max. 105 °C)

Mathis oven test at 200 °C





Example

Components	[phr]
PVC	100,0
ТОТМ	40,0
Filler	20,0
Stabilizer	12,0

Heat ageing at 125 °C

Congo red stability [min]



Congo red stability of high temperature cable stabilized with Baerlocher products remains at high levels even during long-term heat ageing.

• Ca/Zn: Baeropan MC 8890 KA/2

Pb: Baeropan MC 1978 KA



Electrical resistance during water storage

This figure proves the high performance of our Calcium/ Zinc stabilizers during water storage. The k-value is nearly unchanged even after 35 weeks and is therefore comparable with Lead-based systems.

• Ca/Zn: Baeropan MC 8890 KA/2

Pb: Baeropan MC 1978 KA



Transparent Cables

Calcium/Zinc

Baerostab MC 8763/1 CP is a very efficient Calcium/Zinc stabilizer in powder form. It is particulary suited for odour-sensitive applications.



Baerlocher stabilizers ensure reliable service of cables and wires even in demanding applications. They are equally suitable for pigmented and transparent PVC formulations. Low dusting supply forms facilitate safe handling.



Overview

PVC recipes

Maximum service temperature	70 °C	0° 08	90 °C	105 °C/125 °C
PVC, k-value 70	100	100	100	100
Plasticizer	52 phr DEHP	55 phr DIDP	55 phr DIDP	50 phr TOTM
Filler	70 – 80 phr	60 – 80 phr	60 – 80 phr	15 – 20 phr
Pb-stabilizer	3.0 – 3.5 phr	4.5 – 5.5 phr	4,5 – 5,5 phr	8.0 – 12.0 phr
Baeropan	E 292 KA	E or TX 296 KA		MC 1978 KA
		TX 3600 KA	TX 3600 KA	
Ca/Zn-stabilizer	3.0 – 3.5 phr	4.0 – 5.5 phr	4.0 – 5.5 phr	8 – 12 phr
Baeropan	MC or R KA 81/5	MC or R 8703 KA/5	MC or R 8823 KA	MC or R 8553 KA-ST/3
	MC or R 8703 KA/5	MC or R 8850 KA/5	MC or R 8656 KA-ST	MC 8890 KA/2 (125 °C; 12 – 15 phr)
			MC or R 8937 KA	

MC = powder; E, R = granules; TX = pellets





we add character to plastics

Disclaimer

of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to Information or the product to which Information refers In no event, will Baerlocher be responsible or liable for any loss of profits, lost goodwill, direct, ntellectual property right, and Baerlocher makes no representation or warranty, express or implied, that the use thereof will not infringe any patent or intellectual property rights. No representations or warranties, either express or implied warranties as to the completeness or accuracy of Information. Information is supplied upon the condition that the persons or entities receiving same will make their own determination as to its suitability for their purposes Notice: Although the information and recommendations contained in this document (hereinatter "Information") are presented in good faith and believed to be correct at the date of their publication, Baerlocher makes no representations or eliance upon Information or the product to which Information refers. Nothing contained in this disclaimer is to be construed as a recommendation to use any product, process, equipment or formulation in conflict with any patent or special, indirect, incidental, or consequential damages of any nature whatsoever, including without limitation lost revenue, resulting from the use of or prior to their use.

October 2017



Reach out for the Future: www.baerlocher.com

Please download the following brochures from our webpage:

Baerlocher Additives for PVC

- Cables and Wires
- Calendered Films and Sheets
- Extrusion and Injection Moulding
- Lubricants
- Organotin Stabilizers
- Plastisol
- Sheets and Foamed Profiles

Baerlocher Special Additives

- Metallic Stearates
- Hydrophobic Agents for Building Materials

BÆRLOCHER



Baerlocher GmbH Freisinger Str. 1 85716 Unterschleissheim Germany phone: +49/89 14 37 30 fax: +49/89 14 37 33 12 info@baerlocher.com www.baerlocher.com